

**SOTTER ENGINEERING CORPORATION**  
Floor Slip Resistance Consultants

26705 Loma Verde, Mission Viejo, CA 92691  
Telephone: 949-582-0889 FAX: 949-916-2193  
Email: [info@SafetyDirectAmerica.com](mailto:info@SafetyDirectAmerica.com)  
[www.SafetyDirectAmerica.com](http://www.SafetyDirectAmerica.com)

*Licensed by the State of California  
Board of Professional Engineers  
And Land Surveyors*

*Certified by the City of Los Angeles  
as an official slip resistance testing  
laboratory for flooring*

**CERTIFIED**

**Flooring Slip Resistance Test Results**

Client: **GS Schmitt GmbH**

Report date: 9/5/19

Flooring: **aMbooo**

Page 1 of 3

Sample no.: 1909-0321

Date tested: 9/3/19

Sample Size: 12"x5.5" How and when sample obtained: supplied by client on 8/30/19

Figure 1 shows (one of) the sample(s). Red, green, blue, and white color references are included, with a U.S. penny (1/16 inch thick) for scale. The back of the tile is included to aid in positive identification.



Figure 1: (clockwise from top left) front, back and close-up of sample tested

*This test report shall not be reproduced except in full without  
the written approval of Sotter Engineering Corporation*

### **AS HB198:2014 (AS/NZS 4586) Pendulum Test**

The pendulum is the national standard test device for pedestrian slip resistance in at least 50 nations on five continents and has been endorsed by Ceramic Tile Institute of America since 2001. It has been in continuous use since 1970 for assessing slip resistance of pedestrian surfaces, and is the most widely accepted slip resistance test device worldwide. The trailing edge of a three-inch-wide spring-loaded slider, which is attached to the end of a 20-inch pendulum, contacts the tested surface when the pendulum is released from a horizontal position. The slider contact path length is pre-set to 124-126 mm (approximately 5 inches). The pendulum pushes a pointer that stops and stays at the high point of the pendulum's swing. For more information and video, please visit <https://safetydirectamerica.com/pendulumfloorsliptestng>. The hard Four S ("Standard Shoe Sole Simulating") rubber is generally used for pendulum testing unless the flooring area will be primarily used by barefoot people, in which case the softer TRL rubber may be used. The soft rubber is more representative of bare feet and soft shoe soles, such as is typically found on running shoes.

#### **Pendulum Test Value (PTV), as received, with Four S (96) hard rubber slider:**

**Dry: 59      Wet: 32**

High Pendulum Test Values indicate potentially good traction. AS HB 198: 2014 recommends a range of situation-specific minimum Pendulum Test Values as shown in the attached table below. The Ceramic Tile Institute of America (CTIOA) and United Kingdom Slip Resistance Group (UKSRG) make a more general recommendation and say that a **minimum** pendulum test value of **36** for level floors is considered "low slip potential". According to CTIOA and UKSRG, values of 25-35 are classed as "moderate slip potential". Values of 0-24 have "high slip potential". Slip resistance can be affected by factors such as floor coatings, abrasives, detergents, contamination, chemical treatments, and wear.

Respectfully submitted,  
SOTTER ENGINEERING CORPORATION



J. George Sotter, P.E., Ph.D.  
President



Building or walkway type	Line no.	Location or function of area	Minimum wet PTV (or BPN)	
			Hard rubber slider	Soft rubber slider
External pavements and ramps	1	External ramps with slopes steeper than 1 in 14 (4.1 degrees)	55	45
	2	External ramps, slopes less than 1 in 14	45	40
	3	Level surfaces: external sales areas (e.g. markets), external car parks, external colonnades, walkways, pedestrian crossings, balconies, verandas, carports, driveways, courtyards, roof decks	45	40
	4	Car parks, undercover	35	35
Hospitals and aged care facilities	5	Bathrooms and ensuites in hospitals and aged care facilities	35	35
	6	Wards and corridors in hospital and aged care facilities	25	20
Hotels, offices, public buildings, schools, kindergartens; entries and access areas including common areas, internal elevator lobbies	7	Dry area	12	NS
	8	Hotel bathrooms, ensuites and toilets	25	20
	9	Hotel kitchens and laundries	25	20
	10	Restroom facilities in offices, bars and shopping centers	35	35
	11	Transitional areas, intended to be kept dry	25	20
	12	Wet area	35	35
Kitchens (commercial), serving areas, cold stores	13	Commercial kitchens	55	45
	14	Serving areas behind bars in bars and clubs	45	40
	15	Cold stores and freezers	45	40
Loading docks	16	Loading docks under cover	55	45
Sports stadiums	17	Undercover concourse areas	35	35
Supermarkets and shopping centers	18	Dry areas in separate shops in shopping centers	12	NS
	19	Fast food outlets, buffet food servery areas, food courts and fast food dining areas in shopping centers	35	35
	20	Fresh fruit and vegetable areas in shops and supermarkets	35	35
	21	Shop entry areas with external entrances	35	35
	22	Supermarket aisles (except fresh food areas)	12	NS
	23	Wet areas in separate shops in shopping centers	35	35
Swimming pools and sporting facilities	24	Communal changing rooms	35	35
	25	Communal shower rooms	45	40
	26	Swimming pool decks	45	40
	27	Swimming pool ramps and stairs leading to water	55	45
Stairs	28	Dry treads or landings	35	35
	29	Wet treads or landings	45	40
NS - not specified				

Table 1. Recommended minimum PTV from the June 2014 Australian standard. The minimum values in this table are both more permissive (values below 36) and more conservative (values above 36) than the CTIOA and UKSRG standards discussed on the previous page. We consider the standard summarized on this page to be the world's most sophisticated. However, the choice between the two is left to the reader.